

NOVOCON® HE05535

PRODUCT DATA SHEET

NOVOCON® HE05535 STEEL FIBRE

Novocon® HE05535, steel fibres are designed specifically for the reinforcement of concrete, mortars and other cementitious mixes. Novocon® HE05535 is a cold drawn wire fibre, deformed with hooked ends to provide optimum performance within the concrete mix. Novocon® HE05535 steel fibres are European Standard EN 14889-1:2006 compliant and have been specifically designed to meet or exceed the defined performance requirements .

FEATURES & BENEFITS

- Provides uniform multi-directional concrete reinforcement
- Increases crack resistance, ductility, energy absorption or toughness of concrete
- Improves impact resistance, fatigue endurance and shear strength of concrete
- High tensile strength fibre bridging joints and cracks to provide tighter aggregate interlock resulting in increased load carrying capacity
- Provides increased ultimate load bearing capacity which allows possible reduction of concrete section
- Requires less labour to incorporate into concrete than conventional reinforcement
- Offers economical concrete reinforcement solutions with greater project scheduling accuracy
- Ideally suited for hand or vibratory screeds, laser screeds and all conventional finishing equipment

PRIMARY APPLICATIONS

- Sprayed concrete
- Precast
- Overlays and screeds

COMPLIANCE

- Complies with European Standard EN 14889-1:2006 Fibres for Concrete Part 1: Group I and carries CE marking
- Conforms to ASTM A820/A820M-04 Standard Specification for Steel Fibers for Fiber Reinforced Concrete. Type I cold drawn wire

PHYSICAL PROPERTIES

Fibre Length	35 mm
Fibre Diameter	0.55 mm
Aspect Ratio	64
Tensile Strength	1450 N/mm ²
Deformation	Hook End
Appearance	Bright and clean wire

NOVOCON® HE05535

PRODUCT USE

MIXING DESIGNS AND PROCEDURES: Novocon® HE05535 steel fibres can be added during or after the batching of the concrete but should never be added as the first component. Such devices as conveyor belts, chutes and dispensers may be used to add fibres to the mixer at the ready mix plant. After the fibres have been added, the concrete should be mixed for sufficient time (minimum 5 minutes at full mixing speed) to ensure uniform distribution of the fibres throughout the concrete. The use of mid or high-range water reducing admixtures can be advantageous, but is not essential.

PLACING: Novocon® HE05535 steel fibres can be pumped and placed using conventional equipment. Hand or vibratory screeds and laser screeds can be used with Novocon® HE05535 steel fibres.

FINISHING: Conventional finishing techniques and equipment can be used when finishing Novocon® HE05535 steel fibre concrete. In some cases an extra bull float process is advised and lowering the angle of the power float blades will help to minimize fibre exposure on the surface.

DOSAGE RATE: The fibre dosage will vary depending on the type of application, concrete mix design and the performance/ toughness requirements of each particular project. Typically, steel fibre dosage will be in the range of 20 kg to 40 kg per cubic meter. Propex Concrete Systems technical staff can offer advice on dosage requirements once performance requirements have been established by the project designer/engineer.

COMPATIBILITY

Novocon® HE05535 steel fibres are compatible with all curing compounds, super plasticizers, water reducers, hardeners and coatings.

SAFETY

It is recommended that gloves and eye protection be used when handling or adding Novocon® HE05535 steel fibres to concrete.

PACKAGING

Novocon® HE05535 fibres are available, as standard, in 25 kg boxes. They are also available upon request in 1000 kg bulk bags. The pallets should be protected against rain and snow. Do NOT stack pallets on top of each other.

TECHNICAL SERVICES

Propex Concrete Systems is backed by our team of reinforced concrete specialists who can carefully analyze each project and provide fibre reinforced concrete design solutions to ensure maximum project performance and cost efficiency.

REFERENCES

- European Standard EN 14889 -1:2006 Fibres for Concrete
- ASTM A820/A820M-04 Standard Specification for Steel Fibers for Fiber Reinforced Concrete.
- ASTM C1116/C1116M Standard Specification for Fiber-Reinforced Concrete.
- ASTM C1399 Standard Test Method for Obtaining Average Residual-Strength of Fiber Reinforced Concrete.
- ASTM C1550 Standard Test Method for Flexural Toughness of Fiber Reinforced Concrete (Using centrally loaded round panel).
- ASTM C1609/C1609M Standard Test Method for Flexural Performance of Fiber-Reinforced Concrete. (Replaces ASTM C1018)
- JCI-SF4 Method of Test for Flexural Strength and Flexural Toughness of Fiber Reinforced Concrete.
- Concrete Society (UK) Technical Report 63 Guidance for the Design of Steel Fibre Reinforced Concrete
- Concrete Society (UK) Technical Report 34 Concrete Industrial Floors
- Concrete Society (UK) Technical Report 66 External In-situ Concrete Paving
- Publication N° 7 Norwegian Concrete Association
- EFNARC European Specification for Sprayed Concrete

SPECIFICATION CLAUSE

Fibres for concrete shall be Novocon® HE055350 hooked end steel fibres conforming to EN 14889-1:2006 Group I and manufactured from cold drawn wire with a minimum tensile strength of 1450 N/mm².

Unless otherwise stated Novocon® HE05535 steel fibres shall be added to the concrete at the recommended application rate ofkg per cubic metre and mixed for sufficient time (minimum 5 minutes at full mixing speed) to ensure uniform distribution of the fibres throughout the concrete.

Fibrous concrete reinforcement shall be manufactured by:

Propex Concrete Systems, Propex House, 9 Royal Court, Basil Close, Chesterfield, Derbyshire, S41 7SL, United Kingdom.
Telephone: + 44 (0) 1246 564200, Fax: + 44 (0) 1246 564201,
e-mail: enquiries@propexinc.co.uk



USA
4019 Industry Drive
Chattanooga, Tennessee 37416
TEL: (423) 892-8080
FAX: (423) 892-0157

INTERNATIONAL
Propex House, 9 Royal Court, Basil Close,
Chesterfield, Derbyshire, S41 7SL, UK
TEL: +44 (0) 1246 564200
FAX: +44 (0) 1246 564201

www.fibermesh.com

"Fibermesh", "Novomesh", "Novocon", "ENDURO" and "e3" are registered trademarks of Propex Concrete Systems Corp.

THIS PUBLICATION SHOULD NOT BE CONSTRUED AS ENGINEERING ADVICE. WHILE INFORMATION CONTAINED IN THIS PUBLICATION IS ACCURATE TO THE BEST OF OUR KNOWLEDGE, PROPEX DOES NOT WARRANT ITS ACCURACY OR COMPLETENESS. THE ULTIMATE CUSTOMER AND USER OF THE PRODUCTS SHOULD ASSUME SOLE RESPONSIBILITY FOR THE FINAL DETERMINATION OF THE SUITABILITY OF THE INFORMATION AND THE PRODUCTS FOR THE CONTEMPLATED AND ACTUAL USE. THE ONLY WARRANTY MADE BY PROPEX FOR ITS PRODUCTS IS SET FORTH IN OUR PRODUCT DATA SHEETS FOR THE PRODUCT, OR SUCH OTHER WRITTEN WARRANTY AS MAY BE AGREED BY PROPEX AND INDIVIDUAL CUSTOMERS. PROPEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ARISING FROM PROVISION OF SAMPLES, A COURSE OF DEALING OR USAGE OF TRADE.

© 2008 Propex Concrete Systems Corp. CS/INT - 570 07/08