



# Sikafloor® Multicryl

## Water Based Coloured Acrylic Sealer

### Technical Data Sheet

#### DESCRIPTION

**Sikafloor Multicryl** is a one component matt finish water based acrylic sealer for concrete.

#### USES

- \* Basements.
- \* Exhibition rooms.
- \* Balconies.
- \* Staircases.
- \* Light industrial use.

#### ADVANTAGES

- \* One component.
- \* Indoor and outdoor use.
- \* Easy application.
- \* Quick overcoatability.
- \* Good hiding power.
- \* Brush or roller application.

#### Technical Data (typical)

**Colour:** Refer to colour chart and current price list for availability and minimum order quantities.

**Density (SG):** 1.35 kg/litre

**Volume solids:** 46.5%

**Application temperatures & humidity conditions:** +10°C min, +30°C max (Substrate and ambient)  
RH 75% max

**CHEMICAL RESISTANCE:** Diesel fuel and engine oil

**Additional application information:** +10°C +20°C +30°C

#### Waiting time between coats:

<b>Sikafloor 156</b>	min 24 hrs	12 hrs	8 hrs
	max 6 days	4 days	2 days
<b>Sikafloor Multicryl</b>	min 24 hrs	7 hrs	5 hrs
	max 7 days	5 days	5 days

#### Final drying times:

<b>Foot traffic</b>	24 hrs	7 hrs	5 hrs
<b>Fully serviceable</b>	4 days	2 days	1.5 days

All above values are approximate.

### SYSTEM TABLE

Use / Product	Light wear	Approx consumption per coat	Friable substrates	Approx consumption per coat
Primer coat	1 x <b>Sikafloor Multicryl</b> + 30% water	approx 0.15-0.2 kg/m <sup>2</sup> approx 0.1-0.15 ltr/m <sup>2</sup>	1 x <b>Sikafloor 156</b>	approx 0.3-0.5 kg/m <sup>2</sup>
Sealer coat	2 x <b>Sikafloor Multicryl</b>	approx 0.25 kg/m <sup>2</sup> approx 0.2 ltr/m <sup>2</sup>	2 x <b>Sikafloor Multicryl</b>	approx 0.25 kg/m <sup>2</sup> approx 0.2 ltr/m <sup>2</sup>

## SURFACE PREPARATION

The cementitious substrate should be sound and of sufficient compressive strength. ( Min 25 N/ mm<sup>2</sup> ) . Minimum pull off strength 1.5 N/mm<sup>2</sup>.

The surfaces must be dry and free of all contaminants eg oils, grease, surface treatments and coatings etc. The substrate must be prepared mechanically to achieve an open textured fine gripping surface, free of cement laitance. Weak concrete should be removed and surface defects such as blowholes and voids must be fully exposed.

All dust, loose and friable material must be completely removed from all surfaces before application of the coating preferably by brush and vacuum.

Repairs to cementitious substrate and filling of blowholes levelling of irregularities etc should be carried out using an appropriate product from the **SikaDur**<sup>®</sup>, **Sikafloor**<sup>®</sup> or **SikaGard**<sup>®</sup> range of materials.

## MIXING

Mix thoroughly with a slow speed electric stirrer (300-400 rpm).

## APPLICATION

Apply **Sikafloor Multicryl** onto primed substrate by brush or roller at the required consumption.

## IMPORTANT NOTES

- \* Always ensure good ventilation when using **Sikafloor Multicryl** in a confined space.
- \* Freshly applied **Sikafloor Multicryl** should be protected from damp, condensation and water for at least 24 hours.
- \* Avoid puddles on surface.
- \* Not recommended for vehicular trafficking.

## CLEANING EQUIPMENT

Use water. Hardened material may have to be mechanically removed.

## PACKAGING

Refer to latest price list

## CONSUMPTION

Approximately 0.25 kg/m<sup>2</sup> (0.20 litres/m<sup>2</sup>). These figures do not allow for surface porosity, profile or wastage.

## STORAGE AND SHELF LIFE

Minimum 12 months in sealed containers stored in dry warehouse conditions (+5°C - +25°C).



**Sika**®

### Handling Precautions

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

### Important Note

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

**Please consult our Technical Sales Department for further information**

SIKA LIMITED

Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ

Tel: 01707 394444 Email: [sika@uk.sika.com](mailto:sika@uk.sika.com)

Fax: 01707 329129 [www.sika.com](http://www.sika.com)

