



# Sikafloor<sup>®</sup> 261 Thixo

## Solvent Free Textured Coloured Epoxy Coating

### Technical Data Sheet

#### DESCRIPTION

**Sikafloor 261 Thixo** is a two component textured, coloured solvent free epoxy floor coating. It can be used to create textured coatings for medium duty use in industry as a coating to concrete and cementitious screeds.

#### USES

- \* Manufacturing areas.
- \* Wet and dry process areas.
- \* Laboratories.
- \* Production areas.
- \* Storage areas.
- \* Plant rooms.
- \* Clean rooms.
- \* Cold rooms.
- \* Work areas.

#### ADVANTAGES

- \* Textured surface profile.
- \* Versatile - one product for many applications.
- \* High mechanical properties.
- \* Good abrasion resistance.
- \* Good chemical resistance.
- \* High durability.
- \* Coloured.
- \* Solvent free.
- \* Safe to use.
- \* Easy and fast to apply - low viscosity.
- \* Easily cleaned and maintained.
- \* Waterproof.

#### FLOOR COATING SYSTEM:

|                              |   |
|------------------------------|---|
| <b>Normal substrate:</b>     | 1 x <b>Sikafloor 156.</b><br>1 - 2 x <b>Sikafloor 261 Thixo.</b>  |
| <b>Dense substrate:</b>      | 1 x <b>Sikafloor 2420.</b><br>1 - 2 x <b>Sikafloor 261 Thixo.</b> |
| <b>Material consumption:</b> | Approx 0.5 - 1.2 kg/m <sup>2</sup><br>per coat.                   |

#### Technical Data (typical)

|  |   |
|--|---|
| <b>Colour:</b>   | Refer to colour chart and current price list for availability and minimum order quantities.           |
| <b>Density (SG):</b>                                       | Approx 1.4 kg/litre   |
| <b>Volume solids:</b>                                      | Approx 100%   |
| <b>Application temperatures &amp; humidity conditions:</b> | +10°C min, +30°C max<br>(Substrate and ambient)<br>RH 80% max   |
| <b>Substrate M.C. &amp; RH:</b>                            | ≤4% by Wt or ≤75% RH  |
| <b>CHEMICAL RESISTANCE:</b>                                | Refer to chart<br>(Consult Sika Ltd for additional information).                                      |
| <b>Additional application information:</b>                 | +10°C   +20°C   +30°C   |
| <b>Pot life:</b>   | 60 mins   40 mins   15 mins   |
| <b>Waiting time between coats:</b>                         | min                      30 hrs   24 hrs   12 hrs<br>max                      3 days   2 days   1 day |
| <b>Final drying times:</b>                                 |   |
| <b>Foot traffic</b>  | 3 days   2 days   1 day   |
| <b>Lightly serviceable</b>                                 | 6 days   4 days   2 days  |
| <b>Fully serviceable</b>                                   | 10 days   7 days   5 days   |

All above values are approximate.

## SURFACE PREPARATION

The cementitious substrate should be sound and of sufficient compressive strength. ( Min 25 N/ mm<sup>2</sup> ) .  
Minimum pull off strength 1.5 N/mm<sup>2</sup>.

The surfaces must be dry and free of all contaminants eg oils, grease, surface treatments and coatings etc. The substrate must be prepared mechanically to achieve an open textured fine gripping surface, free of cement laitance. Weak concrete should be removed and surface defects such as blowholes and voids must be fully exposed.

All dust, loose and friable material must be completely removed from all surfaces before application of the coating preferably by brush and vacuum.

Repairs to cementitious substrate and filling of blowholes levelling of irregularities etc should be carried out using an appropriate product from the **SikaDur**<sup>®</sup>, **Sikafloor**<sup>®</sup> or **SikaGard**<sup>®</sup> range of materials.

## MIXING

Prior to mixing, stir component A (resin), add all of component B (Hardener) and mix both components thoroughly with a low speed electric stirrer (300-400 rpm) for a minimum of 3 minutes until a uniform mix has been achieved. Leave material to stand in container until the majority of air bubbles have dispersed.

## APPLICATION

Prior to application, confirm substrate moisture content and RH. If >4% by wt & >75% RH. **Sikafloor**<sup>®</sup> **EpoCem**<sup>®</sup> may be applied as a D.P.M. system

Apply mixed **Sikafloor 261 Thixo** to the primed substrate by roller or squeegee. Back roller to achieve even coverage and finish with a textured roller to achieve the desired peak trough amplitude.

## IMPORTANT NOTES

- \* Construction joints require pre treatment with a stripe coat. Contact **Sika Ltd** for further details.
- \* Do not apply **Sikafloor 261 Thixo** on substrates in which significant vapour pressure may occur.
- \* Both **Sikafloor 261 Thixo** and **Thinner C** are flammable. NO NAKED FLAMES.
- \* Always ensure good ventilation when using **Sikafloor 261 Thixo** in a confined space.
- \* Quartz silica sand can be sprinkled on to **Sikafloor 261 Thixo** then sealed to form a slip resistance surface
- \* Freshly applied **Sikafloor 261 Thixo** should be protected from damp, condensation and water for at least 24 hours.
- \* Avoid puddles on surface.
- \* Blending a small quantity of suitable quartz sand (10%) with the product at the time of mixing allows an increased microtexture (slip resistance) to be achieved on the finished surface.

## CLEANING EQUIPMENT

Use **Thinner C**. Hardened material may have to be mechanically removed.

## PACKAGING

Refer to latest price list

## CONSUMPTION

Approximately 0.5 - 1.2 kg/m<sup>2</sup> dependent upon required surface profile. (These figures do not allow for surface porosity, profile or wastage).

Maximum yield per pack - refer to latest price list.

## STORAGE AND SHELF LIFE

Minimum 1 year in sealed containers stored in dry warehouse conditions (+5°C - +25°C).

### Handling Precautions

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

### Important Note

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

Please consult our Technical Sales Department for further information

SIKA LIMITED

Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ

Tel: 01707 394444 Email: sika@uk.sika.com

Fax: 01707 329129 www.sika.com

