



Sikasil® C

One Part General Purpose Silicone Sealant

Technical Data Sheet

DESCRIPTION

Sikasil C is a one part general purpose silicone sealant.

USES

Sikasil C is suitable for providing weatherproof elastic joints between a variety of substrates.

- * Glass.
- * Metals.
- * Wood.
- * Ceramic tiles.
- * Acrylics/polycarbonates.

ADVANTAGES

- * Low odour.
- * 100% silicone.
- * Non corrosive.
- * Good fungal resistance.
- * Excellent UV resistance.

Technical Data (typical)

Colour:	White
Density:	1.5 kg/litre
Movement Accommodation Factor (MAF):	25%
Service temperatures: Range:	-50°C to +150°C
Cure rate:	2 mm/day (+23°C / 50% RH)
Application temperature:	+5°C min, +35°C max (Substrate and ambient)
Shore A hardness:	29 after 28 days
Tack free time:	30 mins - hour (+23°C / 50% RH)
Elastic recovery:	> 90%
Maximum joint width:	25.0 mm
Minimum joint depth for expansion joints:	6.0 mm
Modulus:	< 0.43 N/mm ² @ 100% elongation
Complies with the performance standards of:	BS5889:1989

All above values are approximate.

SURFACE PREPARATION

All surfaces must be sound, clean, dry and free from any surface contaminants.

All loose particles, paint, laitance, rust and other poorly adhering materials should be removed by suitable hand or mechanical preparation techniques.

Iron and steel should be protected by an anti-corrosion primer such as **Icosit® EG1** prior to joint sealing.

PRIMING

Primer is not required.

APPLICATION

- * Insert **Sika® Joint Backing Rod** to required depth.
- * Apply appropriate primer to joint sides and observe waiting time before application of **Sikasil C**.
- * Insert cartridge or sausage into sealant gun and firmly extrude **Sikasil C** into the joint making sure that it is in full contact with the sides of the joint.
- * Fill the joint, avoiding air entrapment.
- * **Sikasil C** should be tooled to a smooth finish within 5 minutes.

Also refer to BASA/CIRIA application guidelines.

Masking tape should be used where sharp exact joint lines or exceptionally neat lines are required. Remove the tape whilst the sealant is still soft.

JOINT DESIGN

Refer to BASA/CIRIA Guidelines. (CIRIA Publication 80) and current British Standards.

IMPORTANT CONSIDERATIONS

- * **Sikasil C** should not be used for structural glazing.
- * **Sikasil C** releases acetic acid during curing and can corrode sensitive metals including mirror silver.
- * Protect the finished joint from water for at least 2 hours.
- * **Sikasil C** should not be used in submerged conditions or where physical abuse and/or abrasion is likely to take place.
- * **Sikasil C** may not be overpainted.
- * **Sikasil C** is not recommended for porous substrates such as marble, concrete, stone and granite.
- * **Sikasil C** is not suitable for food contact applications.
- * Do not use **Sikasil C** in contact with materials containing bitumen, pitch, natural rubble, EPDM or other materials which may bleed oils, plasticisers or solvents.

CLEANING

Clean tools immediately with **Sika Thinner C**.

PACKAGING

Refer to latest price list.

CONSUMPTION

Theoretical consumption of **Sikasil C** per 310cc sausage (without wastage):

$$\text{Length of joint (m)} = \frac{310}{\text{Joint width (mm)} \times \text{joint depth (mm)}}$$

$$\text{Litres/metre run of joint} = \frac{\text{Joint width (mm)} \times \text{joint depth (mm)}}{1000}$$

$$\text{No of cartridges / sausages required for joint} = \frac{\text{Joint width (mm)} \times \text{joint depth (mm)} \times \text{length (m)}}{\text{volume of cartridge (ml)}}$$

STORAGE AND SHELF LIFE

18 months from date of production if stored in cool, dry conditions (@ +5°C to +25°C).

Handling Precautions

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

Important Note

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

Please consult our Technical Sales Department for further information

SIKA LIMITED

Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ

Tel: 01707 394444 Email: sika@uk.sika.com

Fax: 01707 329129 www.sika.com

