



# Icosit® EG1

## MIO Epoxy Intermediate/Primer

### Technical Data Sheet

#### DESCRIPTION

Icosit EG1 is a two component epoxy resin system containing micaeous iron oxide providing a high build chemically and abrasion resistant coating direct to new or weathered galvanized and an intermediate coating for steel.

#### USES

- \* Bridges.
- \* Submerged/non submerged structures.
- \* Harbour and port facilities.
- \* Water and sewage treatment.
- \* General fabrication.
- \* Street furniture.

#### ADVANTAGES

- \* Direct application to new or weathered galvanized structures.
- \* Fast drying.
- \* High build intermediate coating .
- \* Highly abrasion/chemical resistant travel coats.
- \* Three coat system application possible within one working day.
- \* Does not require 'T' wash or etch primer when applied direct to new or weathered galvanized substrates.

#### Technical Data

<b>Colour:</b>	Several shades of grey/white		
<b>Finish:</b>	Matt		
<b>Density (SG):</b>	1.6 kg/litre		
<b>Volume solids:</b>	65%		
<b>Typical film thickness per coat:</b>	80 - 100 microns dry 123 - 153 microns wet		
<b>Application temperatures &amp; humidity conditions:</b>	+5°C minimum (substrate) +3°C (5°F) above the dew point		
<b>Coverage:</b>	8 m <sup>2</sup> /litre @ 80 microns dft		
<b>Service temperature:</b>	Max dry heat +150°C Max damp heat +50°C		
<b>Method of Application:</b>	Airless spray, brush or roller		
<b>Drying times:</b>	<b>10°C</b>	<b>20°C</b>	<b>30°C</b>
Touch dry:	1.5 hours	45 mins	20 mins
Hard dry:	8 hours	6 hours	3 hours
Overcoating:			
Max	3 months	3 months	3 months
<b>Mix ratio: (A:B)</b>	94.7:5.3 by wt		
<b>No of coats:</b>	1 - 2		
In accordance with ISO 12 944 Pt 5			
<b>Pot life: (hours)</b>	<b>10°C</b>	<b>20°C</b>	<b>30°C</b>
	12	8	5
<b>VOC:</b>	347 g/litre		
<b>Flashpoint:</b>	Pt A 23°C Pt B 32°C		

All above values are approximate.

## SURFACE PREPARATION

### Coated surfaces:

**Icosit EG1** is an intermediate/finishing coat which should be applied over a sound, prepared, primed or coated surface.

Test areas in accordance with ISO 129 44 should be carried out to confirm compatibility and adhesion.

The surface to be coated should be dry and free from contaminants, such as dust, oil, grease, algal growth etc.

### Galvanized surfaces:

Refer to **Sika®** Galvanized Steel Duplex Guidelines. Available on request.

## MIXING

Always mix complete units as supplied. Power agitate component A, add component B and completely mix both components.

## APPLICATION

**Airless spray:** Typically 140 - 200 microns per coat wft on vertical surfaces

Tip range 0.33 - 0.43 mm (13 - 17 thou)  
Spray angle 20° - 30°C  
Output fluid pressure at tip  
Min (141 kg/cm<sup>2</sup>) (2000 psi)

**Brush:** Typically 100 - 150 microns per coat wft on vertical surfaces

**Roller:** Typically 100 - 150 microns per coat wft on vertical surfaces

## THINNING

Not recommended unless ambient temperature is below 15°C when up to 5% by volume of **Thinner EG** may be added. Full atomisation should be obtainable using the correct proprietary airless spray equipment without thinning.

## IMPORTANT CONSIDERATIONS

- \* Colour shade may vary from colour cards.
- \* Apply only to dry surfaces.
- \* Do not apply during mist or fog conditions or when snow or rain is imminent.
- \* Avoid condensation on the coating during the initial drying period.
- \* Apply in ventilated areas

## CLEANING OF EQUIPMENT

Use **Thinner EG**. Hardened material may have to be mechanically removed.

## PACKAGING

Refer to latest price list

## CONSUMPTION

Approximately 8 m<sup>2</sup>/litre @ 80 microns dft. These figures do not allow for surface porosity, profile or wastage).

## STORAGE AND SHELF LIFE

Minimum 12 months in sealed containers stored in dry warehouse conditions (+5°C - +25°C).

### Handling Precautions

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

### Important Note

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

Please consult our Technical Sales Department for further information

SIKA LIMITED

Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ

Tel: 01707 394444 Email: sika@uk.sika.com

Fax: 01707 329129 www.sika.com

